

Alekh

PLASTICS TESTING CENTRE

F-94-95, RUDRAKSHA-II, JASHODANAGAR MEHAMDABAD HIGHWAY,
VATVA, AHMEDABAD: 382445. TEL-FAX : 79-25830445,
E-Mail: alekh_plastics@yahoo.com; alekhplastics@gmail.com www.alekhtestingcentre.com

Doc.No: F/RPT/01

Page no: 1 of 1

TEST REPORT

No: TR/20-21/0662

Date of issue: 19/03/2021

Issued to: M/s. Deeya Panel Products Pvt. Ltd.

Date of receipt: 26/02/2021

GIDC Estate,
Ankleshwar

Date of performance of testing: 27/02/21 to 17/03/21

Sampling details: By customer

Sample details: Regenerated plastics composite sheet (as stated by the party)

Sample Packing: Loose Sample condition: Satisfactory Mode of delivery: By courier

Your reference: Received by courier on 26/02/2021

Test condition: 27°C/63% RH

Test result

Sample	Test Property	Unit	Test method	Test value
Sheet as above	Flexural strength(Bending)	MPa	ASTM D 790	11.4
	Thermal resistance	---	At 80°C/30min	No effect
	Adhesive bonding strength	kg	With SR998 after 2hrs.	23
	Resistance to boiling water	---	For 72 hrs immersion	No effect
	Drilling ability	---	With ½" drill/machine drill	Satisfactory
	Dimensional stability	%	At 100°C/30min	-0.09



Authorised Signatory


B. R. Phadnis

Chief Executive

N.B.: No liabilities are accepted, whatsoever, for this test report. Valid only for the sample tested. Not for publication. Not for legal purpose.

~~~~~ END OF REPORT ~~~~~

.....towards making quality feasible!



# Alekh

## PLASTICS TESTING CENTRE

F-94-95, RUDRAKSHA-II, JASHODANAGAR MEHAMDABAD HIGHWAY,  
VATVA, AHMEDABAD: 382445. TEL-FAX : 79-25830445,  
E-Mail: alekh\_plastics@yahoo.com; alekhplastics@gmail.com [www.alekhtestingcentre.com](http://www.alekhtestingcentre.com)

Doc.No: F/RPT/01

Page no: 1 of 1

### TEST REPORT

No: TR/20-21/0662A

Date of issue: 19/03/2021

Issued to: M/s. Deeya Panel Products Pvt. Ltd.

Date of receipt: 26/02/2021

GIDC Estate,

Date of performance of testing: 27/02/21 to 17/03/21

Ankleshwar

Sampling details: By customer

Sample details: Regenerated plastics composite sheet (as stated by the party)

Sample Packing: Loose Sample condition: Satisfactory Mode of delivery: By courier

Your reference: Received by courier on 26/02/2021

Test condition: 27°C/63% RH

### Test result

| Sample         | Test Property               | Unit | Test method                                  | Test value   |
|----------------|-----------------------------|------|----------------------------------------------|--------------|
| Sheet as above | Resistance to acid          | ---  | With 1% H <sub>2</sub> SO <sub>4</sub> /6hrs | No effect    |
|                | Nail holding capacity       | kg   | NA                                           | 16           |
|                | Water absorption            | %    | ASTM D 570                                   | 3.0          |
|                | Swelling in water           | %    | -----do-----                                 | +0.2         |
|                | Sawing & cutting ability    | ---  | With machine saw                             | Satisfactory |
|                | Screw holding capacity-face | kg   | 1/8" self threaded screw                     | 51.2         |
|                | Screw holding capacity-edge | kg   | 1/8" self threaded screw                     | 46           |



Authorised Signatory


B. R. Phadnis

Chief Executive

*N.B.: No liabilities are accepted, whatsoever, for this test report. Valid only for the sample tested. Not for publication. Not for legal purpose.*

~~~~~ END OF REPORT ~~~~~

.....towards making quality feasible!



Alekh

PLASTICS TESTING CENTRE

F-94-95, RUDRAKSHA-II, JASHODANAGAR MEHAMDABAD HIGHWAY,
VATVA, AHMEDABAD: 382445. TEL-FAX : 79-25830445,

E-Mail: alekh_plastics@yahoo.com; alekhplastics@gmail.com www.alekhtestingcentre.com

Doc.No: F/RPT/01

Page no: 1 of 1

TEST REPORT

URL no: TC620921000000069

No: TR/20-21/0662N

Date of issue: 19/03/2021

Issued to: M/s. Deeya Panel Products Pvt. Ltd.

Date of receipt: 26/02/2021

GIDC Estate,
Ankleshwar

Date of performance of testing: 27/02/21 to 17/03/21

Sampling details: By customer

Sample details: Regenerated plastics composite sheet (as stated by the party)

Sample Packing: Loose Sample condition: Satisfactory Mode of delivery: By courier

Your reference: Received by courier on 26/02/2021

Test condition: 27°C/63% RH

Test result

| Sample | Test Property | Unit | Test method | Test value |
|----------------|----------------------------------|--------------------|-------------|--------------|
| Sheet as above | Melting point | °C | ISO: 3146 | 134 |
| | Modulus of elasticity | MPa | ASTM D 638 | 56.1 |
| | Material identification | | | |
| | -presence of phenol formaldehyde | --- | ASTM E 1252 | Not detected |
| | Over all migration | mg/dm ² | EN: 1186 | 2.9 |

The decision rule applied for statement of conformity, for borderline results, considering the uncertainty of measurement is: NOT APPLICABLE. Opinion & interpretation for this report: NOT APPLICABLE




Certificate no: TC-6209
(Accredited for ISO:17025-2017)

Authorised Signatory
B. R. Phadnis
Chief Executive

N.B.: No liabilities are accepted, whatsoever, for this test report. Valid only for the sample tested. Not for publication. Not for legal purpose.

~~~~~ END OF REPORT ~~~~~

.....towards making quality feasible!



# Alekh

## PLASTICS TESTING CENTRE

F-94-95, RUDRAKSHA-II, JASHODANAGAR MEHAMDABAD HIGHWAY,  
VATVA, AHMEDABAD: 382445. TEL-FAX : 79-25830445,

E-Mail: alekh\_plastics@yahoo.com; alekhplastics@gmail.com [www.alekhtestingcentre.com](http://www.alekhtestingcentre.com)

Doc.No: F/RPT/01

Page no: 1 of 1

### TEST REPORT

No: TR/20-21/0662C

Date of issue: 19/03/2021

Issued to: M/s. Deeya Panel Products Pvt. Ltd.

Date of receipt: 26/02/2021

GIDC Estate,

Date of performance of testing: 27/02/21 to 17/03/21

Ankleshwar

Sampling details: By customer

Sample details: Regenerated plastics composite sheet (as stated by the party)

Sample Packing: Loose Sample condition: Satisfactory Mode of delivery: By courier

Your reference: Received by courier on 26/02/2021

Test condition: 27°C/63% RH

### Test result

| Sample         | Test Property         | Unit | Test method        | Test value |
|----------------|-----------------------|------|--------------------|------------|
| Sheet as above | Accelerated UV ageing | ---  | ISO:4892-3/100 hrs | No effect  |



Authorised Signatory

B. R. Phadnis

Chief Executive

*N.B.: No liabilities are accepted, whatsoever, for this test report. Valid only for the sample tested. Not for publication. Not for legal purpose.*

~~~~~ END OF REPORT ~~~~~

.....towards making quality feasible!