

**सिपेट : सेन्टर फॉर स्किलिंग एण्ड
टेक्निकल सपोर्ट (सी एस टी एस)**

रसायन एवं पेट्रोसायन विभाग
रसायन एवं उर्वरक मंत्रालय, भारत सरकार
प्लॉट नं. जे-3/2, एम.आई.डी.सी. औद्योगिक क्षेत्र,
चिकलथाना, औरंगाबाद - 431006
फोन : 0240-2478302-334
फैक्स : 0240-2478333
ईमेल : aurangabad@cipet.gov.in / cipetabad@gmail.com
वेबसाइट : www.cipet.gov.in
मुख्यालय : सिपेट, गिण्डी, चेन्नै-600 032



**CIPET : CENTRE FOR SKILLING AND
TECHNICAL SUPORT (CSTS)**

Department of Chemicals & Petrochemicals,
Ministry of Chemicals & Fertilizers, Govt. of India

Plot No. J-3/2, MIDC Industrial Area,
Chikalathana, Aurangabad - 431006.

Tel. : 0240-2478302-334

Fax : 0240 - 2478333

E-mail : aurangabad@cipet.gov.in / cipetabad@gmail.com

website : www.cipet.gov.in

Head Office : CIPET, Guindy, Chennai-600 032

क्र./सिपेट /औबाद/परीक्षण रिपोर्ट/WO-1503/2020-21/1537/

दिनांक : 08.03.2021

प्रति/ To

DEEYA PANEL PRODUCTS PVT. LTD.
Plot No. 6108/6109 , Opposite Bakul Pharma,
GIDC Ankleshwar, Gujarat- 393001.

विषय: परीक्षण रिपोर्ट- बाबत.

Sub : Test Report – Reg

संदर्भ / Letter Ref: Email Dated 03.02.2021

महोदय / Dear Sir,

कृपया हमारी परीक्षण रिपोर्ट क्रमांक : 23216 & 23217 दिनांक : 08.03.2021 प्राप्त करें।

Please find enclosed herewith the Test Report No. : 23216 & 23217 Dated 08.03.2021.

कृपया संलग्न कस्टमर फीडबैक फार्म भरकर वापस भेजने का कष्ट करें।

Kindly fill the enclosed customer feedback form & return the same.

धन्यवाद / Thanking You,

भवदीय / Yours Sincerely,


कमल जीत घई / Kamal Jit Ghai

निदेशक एवम प्रमुख / Director & Head

संलग्न : उपरोक्तनुसार


Encl : As above

सिपेट : सेन्टर फॉर स्किलिंग एण्ड
टेक्निकल सपोर्ट (सी एस टी एस)

रसायन एवं पेट्रोसायन विभाग
रसायन एवं उर्वरक मंत्रालय, भारत सरकार
प्लॉट नं. जे-3/2, एम.आई.डी.सी. औद्योगिक क्षेत्र,
चिकलथाना, औरंगाबाद - 431006
फोन : 0240-2478302-334
फॅक्स : 0240-2478333
ईमेल : aurangabad@cipet.gov.in / cipetabad@gmail.com
वेबसाईट : www.cipet.gov.in
मुख्यालय : सिपेट, गिण्डी, चेन्नै-600 032



CIPET सि पेट
probe · perform · practice · Plastics



CIPET : CENTRE FOR SKILLING AND
TECHNICAL SUPORT (CSTS)

Department of Chemicals & Petrochemicals,
Ministry of Chemicals & Fertilizers, Govt. of India
Plot No. J-3/2, MIDC Industrial Area,
Chikalhana, Aurangabad - 431006.
Tel. : 0240-2478302-334
Fax : 0240 - 2478333
E-mail : aurangabad@cipet.gov.in / cipetabad@gmail.com
website : www.cipet.gov.in
Head Office : CIPET, Guindy, Chennai-600 032

श्रेणी / : A

क्र. / No.

15745

प्लास्टिक्स परीक्षण केंद्र
PLASTICS TESTING CENTRE

परीक्षण प्रमाण पत्र / TEST CERTIFICATE

Issued to:

DEEYA PANEL PRODUCTS PVT. LTD.
Plot No. 6108/6109 , Opposite Bakul Pharma,
GIDC Ankleshwar, Gujarat- 393001.

Test Report No : 23217
Date : 08.03.2021
Your Ref : Email
Date : 03.03.2021

Page No. 1 of 2

Test Report

PART -A

PARTICULARS OF SAMPLE SUBMITTED

(a) Name of Sample	:	"Regenerated plastic composite sheet" as stated by party
(b) Grade/Variety/Type/Size/Class	:	12 mm -(As sticker on sample)
(c) Declared value, if any	:	Nil
(d) Code No	:	Nil
(e) Batch No. and Date of Manufacturing	:	Nil
(f) Quantity	:	12 mm x 1" x 1" x 6 No's
(g) Mode of Packing	:	Packed in carton
(h) Sealed or not	:	Not Sealed
(i) Date of Receipt	:	13.02.2021
(j) Date (s) of Performance of Test	:	13.02.2021 to 05.03.2021
(k) Any other information	:	Ricron Panels -(As sticker on sample)

PART- B

SUPPLEMENTARY INFORMATION

i) Reference to sampling procedure	:	Samples supplied by the party
ii) Supporting documents for the measurement taken and result derived	:	As given in Part C
iii) Deviation from the test method as prescribed in relevant work instruction, if any -	:	Nil

Pravin R. R.
8/3

Pravin R. R.
08/03/2021



Test Report No : 23217
Date : 08.03.2021

Page No 2 of 2

PART-C				
Test Results				
S.No	Name of the test	Test Method	Unit	Test value obtained
1.	Ash Content	IS 13360 Pt - 8/Sec - 8	%	16.42
2.	Color fastness to light (Xenon arc for 24 hrs)	IS 2454	--	No colour change observed visually
3.	Compressive Strength	IS 13360 Pt - 5/Sec - 8	MPa	6.0
4.	Density	IS 13360 Pt - 3/Sec - 1	g/cc	1.08
5.	Elongation	IS 13360 Pt - 5/Sec - 1	%	4.3
6.	Flame Retardancy	IS13360 Part 6 Sec 5	mm/min	0.00
7.	Flexural Strength	IS 13360 Pt - 5/Sec - 7	MPa	9.1
8.	Modulus of Elasticity (0.1 - 0.3)	IS 13360 Pt - 5/Sec - 1	MPa	739.3
9.	Resistance to Acetone Solvent (6 hrs)	IS 13360 Pt - 8/Sec - 3	%	0.51
10.	Resistance to acid in 2% H2SO4 for 6 hrs	IS 14735	%	1.11
11.	Resistance to Alkali (10% NA ₂ CO ₃ for 6 hrs)	IS 13360 Pt - 8/Sec - 3	%	0.50
12.	Resistance to Benzene Solvent (6 hrs)	IS 13360 Pt - 8/Sec - 3	%	2.24
13.	Resistance to Boiling Water	IS 13360 Pt - 8/Sec - 3	%	0.94
14.	Tensile Strength	IS 13360 Pt - 5/Sec - 1	MPa	6.8
15.	Water Absorption	IS:13360 Part 8 Sec 1	%	0.48
PART D				
Remarks: Nil				
NOTE :	01	This Test Report / Certificate is issued only for the samples submitted to CIPET.		
	02	The results stated above related only to the items tested.		
	03	The quality of the subsequent production lot has to be ensured by the purchaser.		
	04	The reports shall not be reproduced in full / part without written approval of the laboratory.		
	05	Details of tests subcontracted: Nil		

Piyush Kumar
08/03/2021

Piyush Kumar
08/03/2021
Authorized Signatory
Dr. Piyush Kumar
Technical Officer